



中国认可  
国际互认  
检测  
TESTING  
CNAS L0095

TEST REPORT

No.: RZRS2020-0646

Client : Qierling (Beijing) Health Technology Co., Ltd.  
: Address: No 101-42/101-43 (Dongsheng district), 9th Floor, No 1 Building, No 8th , Heiquan Road, Haidian District, Beijing City.

Receiving Date : 2020-09-03                      Completing Date : 2020-09-28

Test Sample : Air sterilizer                      Sample Description : /

Type/Model : Main Inspection Type: DS-X400N  
: Cover Types: Refer to page 3 for details.

Test Items : The content of Lead, Cadmium, Mercury, Hexavalent Chromium, PBBs, PBDEs, DEHP, BBP, DBP, DIBP

Test Method : IEC 62321-3-1:2013, IEC 62321-4:2013, IEC 62321-5:2013,  
: IEC 62321-6:2015, IEC 62321-7-1:2015, IEC 62321-8:2017

Test Conclusion :	According as	Conclusion
	EU Directive 2011/65 and its amendments	Pass

Lu Yating  
Tested by: *Lu Yating*

Zhou Ye  
Reviewed by: *Zhou Ye*

Xia Qingyun  
Title: Director of Engineering Dept.  
Approved by: *Xia Qingyun*

Date of issue: 2020-09-28  
Seal of CVC




Vkan Certification & Testing Co., Ltd.

<b>List of Apparatus</b>					
No.	Test Instrument	Type	Number	Period of Calibration Validity	Used (√)
1	XRF	SEA 1000AII	VG DY-0071	2020.11.24	√
2	ICP-OES	Optima 8300	VG DY-0137	2021.04.17	√
3	UV-VIS	Perkin Elmer Lambda 35	JB-0036	2021.03.10	√
4	GC-MS	Trace 1300-ISQ LT	CL-000363	2020.12.09	√
5	GC-MS	GCMS-QP2010 Plus	NA-0095	2021.09.09	√
6	Analytical Balance	XS204	VG DY-0127	2021.04.01	√

Sample description	<p>According to the declaration of the same material by the customer, except for the different parts, the materials of the parts in the following covered types are consistent with the materials of the parts in the main inspection product type DS-X400N. Covered types: DS-X400W, DS-P400</p> <p>Manufacturer: Qierling (Beijing) Health Technology Co., Ltd. Manufacturer Address: No 101-42/101-43 (Dongsheng district), 9th Floor, No 1 Building, No 8th , Heiquan Road, Haidian District, Beijing City.</p> <p>Factory: Healthlead Corproation Limited Factory Address: Building A, Digital Silicone Valley Industry Park, No. 89, Hengping Road, Henggang Street, Longgang District, Shenzhen, P.R. China</p>
Remark	—

**Flowchart**



**Material list**

Table 1

Component No.	Component name	Specimen No.	Specimen name	No.
1	Shell	1-1	White plastic air intake	1
		1-2	White plastic shell	2
		1-3	White plastic rear cover	3
		1-4	White plastic barn door	4
		1-5	Silvery cladding material (metal screw)(short)	5
		1-6	Silvery base material(metal screw)(short)	6
		1-7	White plastic handle	7
		1-8	Silvery magnet	8
		1-9	Gray plastic bracket	9
		1-10	White plastic cover	10
		1-11	Transparent plastic filter screen	11
		1-12	Gray plastic foundation	12
		1-13	Gray plastic touch panel	13
		1-14	White plastic bracket	14
		1-15	Gray plastic cover	15
		1-16	Black sponge shim	16
		1-17	Gray plastic shell	17
		1-18	Gray plastic bracket	18
		1-19	Gray rubber foot pad	19
		1-20	Gray plastic shell	20
		1-21	Gray plastic cover	21
		1-22	White plastic bracket	22
		1-23	metal screwSilvery cladding material	23
		1-24	metal screwSilvery base material	24
		1-25	metal screwSilvery cladding material	25
		1-26	metal screwSilvery base material	26
		1-27	Silvery metal shim	27

Component No.	Component name	Specimen No.	Specimen name	No.
2	Touch panel	2-1	White plastic bracket	28
		2-2	PCB base material	29
		2-3	Silvery metal soldering tin	30
		2-4	Chip resistance	31
		2-5	Chip capacitance	32
		2-6	Black chip	33
		2-7	Beige plastic connector	34
		2-8	LED light	35
		2-9	Silvery aluminum shell (electrolysis capacitance)	36
		2-10	Black plastic foundation	37
		2-11	Black rubber stuff	38
		2-12	Yellow electrolysis paper	39
		2-13	Gray plastic film	40
3	Displayer	3-1	metal screwSilvery cladding material	41
		3-2	metal screwSilvery base material	42
		3-3	Transparent plastic light block	43
		3-4	Black sponge	44
		3-5	White plastic bracket (display bracket)	45
		3-6	Black coating	46
		3-7	Transparent plastic slice	47
		3-8	PCB base material	48
		3-9	Silvery metal soldering tin	49
		3-10	Chip resistance	50
		3-11	Chip capacitance	51
		3-12	Chip audion	52
		3-13	Black chip	53
		3-14	Beige plastic connector	54
		3-15	LED light(big)	55
		3-16	LED light(small)	56

Component No.	Component name	Specimen No.	Specimen name	No.
3	Displayer	3-17	Silvery aluminum shell (electrolysis capacitance)	57
		3-18	Black plastic foundation	58
		3-19	Black rubber stuff	59
		3-20	Yellow electrolysis paper	60
		3-21	Gray plastic film	61
		3-22	(buzzer)Black plastic shell	62
		3-23	Golden metal slice	63
		3-24	White ceramic coating	64
		3-25	White sponge shim	65
4	Main control panel	4-1	Black plastic shell	66
		4-2	Black plastic cover	67
		4-3	PCB base material	68
		4-4	Silvery metal soldering tin	69
		4-5	Chip resistance	70
		4-6	Chip capacitance	71
		4-7	Chip diode	72
		4-8	Chip audion	73
		4-9	Black chip	74
		4-10	Beige plastic connnector	75
		4-11	White plastic connnector	76
		4-12	White plastic bracket	77
		4-13	Silvery metal Pin	78
		4-14	White fixing glue	79
		4-15	Silvery aluminum shell (electrolysis capacitance)	80
		4-16	Black plastic foundation	81
		4-17	Black rubber stuff	82
4-18	Yellow electrolysis paper	83		
4-19	Gray plastic film	84		
4-20	Silvery metal radiating slice	85		
4-21	Black silicon controlled	86		

Component No.	Component name	Specimen No.	Specimen name	No.
4	Main control panel			
		4-22	Silvery metal fixed screw	87
		4-23	Blue ceramic capacitance1	88
		4-24	Blue ceramic capacitance2	89
		4-25	Blue ceramic capacitance3	90
		4-26	Blue ceramic capacitance4	91
		4-27	Blue ceramic capacitance5	92
		4-28	Black ceramic capacitance	93
		4-29	diode	94
		4-30	Silvery metal jump ring	95
		4-31	Black metal bracket	96
		4-32	Yellow adhesive tape	97
		4-33	Black plastic reel	98
		4-34	Enameled wire	99
		4-35	Yellow plastic shell (safety capacitor)	100
		4-36	Yellow pouring sealant	101
		4-37	Silvery plastic film	102
		4-38	Black silicon controlled	103
		4-39	Black plastic bracket	104
		4-40	Silvery metal fuse wire	105
		4-41	Brown plastic shell	106
		4-42	Black rubber jacket	107
		4-43	Black metal reel	108
		4-44	Enameled wire	109
		4-45	Transparent rubber jacket	110
		4-46	Black rubber jacket	111
		4-47	Yellow adhesive tape	112
		4-48	Black metal bracket	113
4-49	Black plastic reel	114		
4-50	Enameled wire	115		



Component No.	Component name	Specimen No.	Specimen name	No.
4	Main control panel	4-51	Black plastic shell (safety capacitor)	116
		4-52	Silvery metal shell	117
		4-53	Black rubber shim	118
		4-54	Transparent adhesive tape	119
		4-55	Yellow electrolysis paper	120
		4-56	Silvery plastic film	121
		4-57	Black/yellow plastic shell	122
		4-58	Blue plastic shell	123
5	Electrical machine	5-1	Gray plastic bracket	124
		5-2	Black plastic wind wheel	125
		5-3	Silvery cladding material (metal screw)	126
		5-4	Silvery base material (metal screw)	127
		5-5	Silvery cladding material (metal nut)	128
		5-6	Silvery base material (metal nut)	129
		5-7	Silvery cladding material(cushioned screw)	130
		5-8	Silvery base material(cushioned screw)	131
		5-9	Silvery cladding material (metal shim)	132
		5-10	Silvery base material (metal shim)	133
		5-11	Silvery metal fixed slice	134
		5-12	Silvery nameplate paper	135
		5-13	Silvery metal shell	136
		5-14	Black magnet	137
		5-15	Black metal jump ring	138
		5-16	Black metal shim	139
		5-17	Silvery metal axle	140
		5-18	Green coating	141
		5-19	Silvery metal slice	142
		5-20	Enameled wire	143

Component No.	Component name	Specimen No.	Specimen name	No.
5	Electrical machine	5-21	Silvery metal shell	144
		5-22	Silvery metal dust board	145
		5-23	Silvery metal bracket	146
		5-24	Silvery metal ball	147
		5-25	PCB base material	148
		5-26	Silvery metal soldering tin	149
		5-27	Chip resistance	150
		5-28	Chip capacitance	151
		5-29	Chip audion	152
		5-30	Black chip	153
		5-31	Beige plastic connector	154
		5-32	Silvery aluminum shell (electrolysis capacitance)	155
		5-33	Black plastic foundation	156
		5-34	Black rubber stuff	157
		5-35	Yellow electrolysis paper	158
		5-36	Gray plastic film	159
6	Inside connecting line	6-1	White plastic connector	160
		6-2	Red rubber jacket	161
		6-3	White rubber jacket	162
		6-4	Enameled wire	163
		6-5	Red/white rubber jacket	164
		6-6	Beige plastic connector	165
		6-7	Black rubber heat shrink tubing	166
		6-8	White rubber jacket(thin)	167
		6-9	Black rubber sheath	168
		6-10	Black rubber jacket(thick)	169
		6-11	Red rubber jacket(thick)	170
		6-12	Black heat shrink tubing(thick)	171
		6-13	Black plastic magnetshell	172

Component No.	Component name	Specimen No.	Specimen name	No.
6	Inside connecting line	6-14	White plastic ribbon	173
		6-15	Black magnetosphere	174
		6-16	Black plastic shell (negative-ion generator)	175
		6-17	Black pouring sealant	176
7	Recharge foundation	7-1	Black plastic charging mouth	177
		7-2	Silvery metal Pin	178
		7-3	Red rubber jacket	179
		7-4	Black rubber jacket	180
		7-5	Enameled wire	181
		7-6	Black heat shrink tubing	182
		7-7	Black magnetosphere	183
		7-8	Black rubber sheath	184
8	Filter element	8-1	White plastic cover1	185
		8-2	White plastic cover2	186
		8-3	Black sponge	187
		8-4	White plastic foundation	188
		8-5	White fibre cloth	189
		8-6	Green fibre cloth	190
		8-7	White fixing glue	191
		8-8	Black carbon filter screen	192
		8-9	Transparent plastic filter screen	193
		8-10	PCB base material	194
		8-11	Silvery metal soldering tin	195
		8-12	Chip resistance	196
		8-13	Chip capacitance	197
		8-14	Chip diode	198
		8-15	Black chip	199
		8-16	metal LED light	200
		8-17	Black metal reel	201

Component No.	Component name	Specimen No.	Specimen name	No.
8	Filter element	8-18	Enameled wire	202
9	WiFi module	9-1	PCB base material	203
		9-2	Silvery metal soldering tin	204
		9-3	White plastic socket	205
		9-4	Transparent closed switch	206
		9-5	metal screw Silvery cladding material	207
		9-6	metal screw Silvery base material	208
		9-7	PCB base material	209
		9-8	Silvery metal soldering tin	210
		9-9	Chip resistance	211
		9-10	Chip capacitance	212
		9-11	Chip diode	213
		9-12	Chip audion	214
		9-13	Black rectifier bridge	215
		9-14	White nameplate	216
		9-15	Silvery metal screening can	217
10	Power line	10-1	Gray rubber plug	218
		10-2	White plastic bracket	219
		10-3	Silvery metal illustration	220
		10-4	Gray rubber sheath	221
		10-5	Blue rubber jacket	222
		10-6	Brown rubber jacket	223
		10-7	Enameled wire	224
		10-8	Gray rubber shell	225
		10-9	White plastic bracket	226
		10-10	Golden metal Pin	227
11	PM2.5 laser sensor	11-1	Blue plastic film	228
		11-2	Silvery metal shell	229
		11-3	Black plastic shell	230

Component No.	Component name	Specimen No.	Specimen name	No.		
11	PM2.5 laser sensor	11-4	Black plastic bracket	231		
		11-5	PCB base material	232		
		11-6	Silvery metal soldering tin	233		
		11-7	Chip resistance	234		
		11-8	Transparent glue	235		
		11-9	Black metal body (camera len)	236		
		11-10	Transparent glass camera len	237		
		11-11	Silvery metal spring	238		
		11-12	PCB base material	239		
		11-13	Silvery metal soldering tin	240		
		11-14	Chip resistance	241		
		11-15	Chip capacitance	242		
		11-16	Chip diode	243		
		11-17	Chip audion	244		
		11-18	Black optical pump	245		
		11-19	Black chip	246		
		11-20	Beige plastic connnector	247		
		11-21	Black metal screw	248		
		11-22	Silvery trademark	249		
		11-23	Black plastic shell (impeller)	250		
		11-24	PCB base material	251		
		11-25	Silvery metal soldering tin	252		
		11-26	Black plastic impeller	253		
		11-27	Silvery metal axle	254		
		11-28	Silvery metal shell	255		
		11-29	Black magnet	256		
		11-30	Black cladding material (metal screw)	257		
		11-31	Silvery base material (metal screw)	258		
		12	PCB	12-1	PCB base material	259

Component No.	Component name	Specimen No.	Specimen name	No.
12	PCB	12-2	Silvery metal soldering tin	260
		12-3	Chip resistance	261
		12-4	Black diode	262
		12-5	Black audion	263
		12-6	Black chip	264
		12-7	Silvery metal chip	265
		12-8	Yellow component	266
		12-9	Gray rubber jacket	267
		12-10	Red rubber jacket	268
		12-11	Black rubber jacket	269
		12-12	Enameled wire	270
		12-13	Beige plastic socket	271
		12-14	White plastic buckle	272
		12-15	Silvery metal battery	273
		12-16	PCB base material	274
		12-17	Silvery metal soldering tin	275
		12-18	Chip resistance	276
		12-19	Black chip	277
		12-20	Yellow plastic paper	278
		12-21	Coppery metal terminal	279

## Test Result

Table 2 The determination of Pb, Cd, Hg, Cr(VI), PBBs, PBDEs, DEHP, BBP, DBP, DIBP

No.	Test Sample	Screening Result						Verification Test Result												
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict	
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000 (d)	0.10 $\mu\text{g}/\text{cm}^2$ (e)	1000	1000	1000	1000	1000	1000	1000		
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50		
1	White plastic air intake	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	
2	White plastic shell	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	
3	White plastic rear cover	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	
4	White plastic barn door	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	
5	Silvery cladding material (metal screw)(short)	N.D.	N.D.	N.D.	/	—	V	/	/	/	/	Negative	/	/	/	/	/	/	P	
6	Silvery base material(metal screw)(short)	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	P	
7	White plastic handle	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	
8	Silvery magnet	/	/	/	/	—	V	N.D.	N.D.	N.D.	N.D.	/	/	/	/	/	/	/	P	

No.	Test Sample	Screening Result						Verification Test Result												
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict	
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000 (d)	0.10 $\mu\text{g}/\text{cm}^2$ (e)	1000	1000	1000	1000	1000	1000	1000		
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50		
9	Gray plastic bracket	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
10	White plastic cover	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
11	Transparent plastic filter screen	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
12	Gray plastic foundation	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
13	Gray plastic touch panel	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
14	White plastic bracket	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
15	Gray plastic cover	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
16	Black sponge shim	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
17	Gray plastic shell	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P



No.	Test Sample	Screening Result						Verification Test Result												
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict	
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000 (d)	0.10 µg/cm <sup>2</sup> (e)	1000	1000	1000	1000	1000	1000	1000		
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50		
18	Gray plastic bracket	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	
19	Gray rubber foot pad	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	
20	Gray plastic shell	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	
21	Gray plastic cover	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	
22	White plastic bracket	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	
23	metal screwSilver cladding material	N.D.	N.D.	N.D.	/	—	V	/	/	/	/	Negative	/	/	/	/	/	/	P	
24	metal screwSilver base material	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	P	
25	metal screwSilver cladding material	N.D.	N.D.	N.D.	/	—	V	/	/	/	/	Negative	/	/	/	/	/	/	P	
26	metal screwSilver base material	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	P	

No.	Test Sample	Screening Result						Verification Test Result													
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict		
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000 (d)	0.10 $\mu\text{g}/\text{cm}^2$ (e)	1000	1000	1000	1000	1000	1000	1000			
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50			
27	Silvery metal shim	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P	
28	White plastic bracket	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
29	PCB base material	N.D.	N.D.	N.D.	N.D.	2.2 $\times 10^4$	V	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P
30	Silvery metal soldering tin	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	/	P
31	Chip resistance	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
32	Chip capacitance	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
33	Black chip	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
34	Beige plastic connector	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
35	LED light	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P

No.	Test Sample	Screening Result						Verification Test Result												
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict	
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000 (d)	0.10 µg/cm <sup>2</sup> (e)	1000	1000	1000	1000	1000	1000	1000		
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50		
36	Silvery aluminum shell (electrolysis capacitance)	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
37	Black plastic foundation	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
38	Black rubber stuff	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
39	Yellow electrolysis paper	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
40	Gray plastic film	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
41	metal screwSilvery cladding material	N.D.	N.D.	N.D.	/	—	V	/	/	/	/	Negative	/	/	/	/	/	/	/	P
42	metal screwSilvery base material	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
43	Transparent plastic light block	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
44	Black sponge	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P

No.	Test Sample	Screening Result						Verification Test Result												
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict	
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000 (d)	0.10 µg/cm <sup>2</sup> (e)	1000	1000	1000	1000	1000	1000	1000		
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50		
45	White plastic bracket (display bracket)	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	
46	Black coating	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	
47	Transparent plastic slice	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	
48	PCB base material	N.D.	N.D.	N.D.	N.D.	2.1 × 10 <sup>4</sup>	V	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P	
49	Silvery metal soldering tin	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	P	
50	Chip resistance	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	
51	Chip capacitance	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	
52	Chip audion	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	
53	Black chip	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	

No.	Test Sample	Screening Result						Verification Test Result												
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict	
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000 (d)	0.10 $\mu\text{g}/\text{cm}^2$ (e)	1000	1000	1000	1000	1000	1000	1000		
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50		
54	Beige plastic connector	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
55	LED light(big)	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
56	LED light(small)	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
57	Silvery aluminum shell (electrolysis capacitance)	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
58	Black plastic foundation	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
59	Black rubber stuff	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
60	Yellow electrolysis paper	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
61	Gray plastic film	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
62	(buzzer)Black plastic shell	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P

No.	Test Sample	Screening Result						Verification Test Result													
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict		
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000 (d)	0.10 $\mu\text{g}/\text{cm}^2$ (e)	1000	1000	1000	1000	1000	1000	1000			
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50			
63	Golden metal slice	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P	
64	White ceramic coating	8.6 $\times 10^5$	N.D.	N.D.	N.D.	—	P $\blacktriangle 1$	5.6 $\times 10^5$	/	/	/	/	/	/	/	/	/	/	/	/	P $\blacktriangle 1$
65	White sponge shim	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P
66	Black plastic shell	N.D.	N.D.	N.D.	N.D.	3.5 $\times 10^4$	V	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P
67	Black plastic cover	N.D.	N.D.	N.D.	N.D.	3.6 $\times 10^4$	V	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P
68	PCB base material	N.D.	N.D.	N.D.	N.D.	2.4 $\times 10^4$	V	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P
69	Silvery metal soldering tin	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	/	P
70	Chip resistance	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
71	Chip capacitance	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P

No.	Test Sample	Screening Result						Verification Test Result												
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict	
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000 (d)	0.10 $\mu\text{g}/\text{cm}^2$ (e)	1000	1000	1000	1000	1000	1000	1000		
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50		
72	Chip diode	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
73	Chip audion	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
74	Black chip	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
75	Beige plastic connector	N.D.	N.D.	N.D.	N.D.	4.1 $\times 10^4$	V	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P
76	White plastic connector	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
77	White plastic bracket	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
78	Silvery metal Pin	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
79	White fixing glue	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
80	Silvery aluminum shell (electrolysis capacitance)	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P

No.	Test Sample	Screening Result						Verification Test Result												
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict	
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000 (d)	0.10 $\mu\text{g}/\text{cm}^2$ (e)	1000	1000	1000	1000	1000	1000	1000		
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50		
81	Black plastic foundation	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	
82	Black rubber stuff	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	
83	Yellow electrolysis paper	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	
84	Gray plastic film	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	
85	Silvery metal radiating slice	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	P	
86	Black silicon controlled	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	P	
87	Silvery metal fixed screw	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	P	
88	Blue ceramic capacitance1	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	P	
89	Blue ceramic capacitance2	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	P	



No.	Test Sample	Screening Result						Verification Test Result													
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict		
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000 (d)	0.10 $\mu\text{g}/\text{cm}^2$ (e)	1000	1000	1000	1000	1000	1000	1000			
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50			
90	Blue ceramic capacitance3	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P	
91	Blue ceramic capacitance4	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	/	P
92	Blue ceramic capacitance5	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	/	P
93	Black ceramic capacitance	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	/	P
94	diode	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P
95	Silvery metal jump ring	N.D.	N.D.	N.D.	8.1 $\times 10^4$	—	V	/	/	/	N.D.	/	/	/	/	/	/	/	/	/	P
96	Black metal bracket	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	/	P
97	Yellow adhesive tape	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P
98	Black plastic reel	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P

No.	Test Sample	Screening Result						Verification Test Result												
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict	
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000	0.10 µg/cm <sup>2</sup> (e)	1000	1000	1000	1000	1000	1000	1000		
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50		
99	Enameled wire	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
100	Yellow plastic shell (safety capacitor)	N.D.	N.D.	N.D.	N.D.	2.0 × 10 <sup>4</sup>	V	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P
101	Yellow pouring sealant	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
102	Silvery plastic film	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
103	Black silicon controlled	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
104	Black plastic bracket	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
105	Silvery metal fuse wire	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
106	Brown plastic shell	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
107	Black rubber jacket	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P

No.	Test Sample	Screening Result						Verification Test Result													
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict		
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000 (d)	0.10 µg/cm <sup>2</sup> (e)	1000	1000	1000	1000	1000	1000	1000			
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50			
108	Black metal reel	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P	
109	Enameled wire	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	/	P
110	Transparent rubber jacket	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P	
111	Black rubber jacket	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P	
112	Yellow adhesive tape	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P	
113	Black metal bracket	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	/	P
114	Black plastic reel	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P	
115	Enameled wire	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	/	P
116	Black plastic shell (safety capacitor)	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P	

No.	Test Sample	Screening Result						Verification Test Result													
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict		
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000 (d)	0.10 µg/cm <sup>2</sup> (e)	1000	1000	1000	1000	1000	1000	1000			
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50			
117	Silvery metal shell	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P	
118	Black rubber shim	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
119	Transparent adhesive tape	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
120	Yellow electrolysis paper	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
121	Silvery plastic film	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
122	Black/yellow plastic shell	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
123	Blue plastic shell	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
124	Gray plastic bracket	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
125	Black plastic wind wheel	N.D.	N.D.	N.D.	N.D.	1464	V	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P

No.	Test Sample	Screening Result						Verification Test Result													
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict		
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000 (d)	0.10 µg/cm <sup>2</sup> (e)	1000	1000	1000	1000	1000	1000	1000			
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50			
126	Silvery cladding material (metal screw)	N.D.	N.D.	N.D.	/	—	V	/	/	/	/	Negative	/	/	/	/	/	/	/	P	
127	Silvery base material (metal screw)	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	/	P
128	Silvery cladding material (metal nut)	N.D.	N.D.	N.D.	/	—	V	/	/	/	/	Negative	/	/	/	/	/	/	/	/	P
129	Silvery base material (metal nut)	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	/	P
130	Silvery cladding material(cushioned screw)	N.D.	N.D.	N.D.	/	—	V	/	/	/	/	Negative	/	/	/	/	/	/	/	/	P
131	Silvery base material(cushioned screw)	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	/	P
132	Silvery cladding material (metal shim)	N.D.	N.D.	N.D.	/	—	V	/	/	/	/	Negative	/	/	/	/	/	/	/	/	P
133	Silvery base material (metal shim)	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	/	P
134	Silvery metal fixed slice	N.D.	N.D.	N.D.	1025	—	V	/	/	/	N.D.	/	/	/	/	/	/	/	/	/	P

No.	Test Sample	Screening Result						Verification Test Result													
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict		
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000 (d)	0.10 $\mu\text{g}/\text{cm}^2$ (e)	1000	1000	1000	1000	1000	1000	1000			
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50			
135	Silvery nameplate paper	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	
136	Silvery metal shell	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	/	P
137	Black magnet	/	/	/	/	—	V	N.D.	N.D.	N.D.	N.D.	/	/	/	/	/	/	/	/	/	P
138	Black metal jump ring	N.D.	N.D.	N.D.	1875	—	V	/	/	/	N.D.	/	/	/	/	/	/	/	/	/	P
139	Black metal shim	N.D.	N.D.	N.D.	1748	—	V	/	/	/	N.D.	/	/	/	/	/	/	/	/	/	P
140	Silvery metal axle	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	/	P
141	Green coating	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
142	Silvery metal slice	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	/	P
143	Enameled wire	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	/	P

No.	Test Sample	Screening Result						Verification Test Result												
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict	
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000 (d)	0.10 $\mu\text{g}/\text{cm}^2$ (e)	1000	1000	1000	1000	1000	1000	1000		
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50		
144	Silvery metal shell	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
145	Silvery metal dust board	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
146	Silvery metal bracket	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
147	Silvery metal ball	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
148	PCB base material	N.D.	N.D.	N.D.	N.D.	$2.5 \times 10^4$	V	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P
149	Silvery metal soldering tin	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
150	Chip resistance	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
151	Chip capacitance	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
152	Chip audion	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P

No.	Test Sample	Screening Result						Verification Test Result												
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict	
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000 (d)	0.10 $\mu\text{g}/\text{cm}^2$ (e)	1000	1000	1000	1000	1000	1000	1000		
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50		
153	Black chip	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
154	Beige plastic connector	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
155	Silvery aluminum shell (electrolysis capacitance)	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
156	Black plastic foundation	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
157	Black rubber stuff	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
158	Yellow electrolysis paper	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
159	Gray plastic film	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
160	White plastic connector	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
161	Red rubber jacket	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P



No.	Test Sample	Screening Result						Verification Test Result													
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict		
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000 (d)	0.10 $\mu\text{g}/\text{cm}^2$ (e)	1000	1000	1000	1000	1000	1000	1000			
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50			
162	White rubber jacket	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	
163	Enameled wire	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	/	P
164	Red/white rubber jacket	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
165	Beige plastic connector	N.D.	N.D.	N.D.	N.D.	4.7 $\times 10^4$	V	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P
166	Black rubber heat shrink tubing	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
167	White rubber jacket(thin)	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
168	Black rubber sheath	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
169	Black rubber jacket(thick)	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
170	Red rubber jacket(thick)	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P

No.	Test Sample	Screening Result						Verification Test Result												
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict	
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000 (d)	0.10 $\mu\text{g}/\text{cm}^2$ (e)	1000	1000	1000	1000	1000	1000	1000		
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50		
171	Black heat shrink tubing(thick)	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
172	Black plastic magnetshell	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
173	White plastic ribbon	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
174	Black magnetosphere	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
175	Black plastic shell (negative-ion generator)	N.D.	N.D.	N.D.	N.D.	$1.8 \times 10^4$	V	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P
176	Black pouring sealant	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
177	Black plastic charging mouth	N.D.	N.D.	N.D.	N.D.	4027	V	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P
178	Silvery metal Pin	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
179	Red rubber jacket	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P

No.	Test Sample	Screening Result						Verification Test Result													
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict		
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000 (d)	0.10 $\mu\text{g}/\text{cm}^2$ (e)	1000	1000	1000	1000	1000	1000	1000			
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50			
180	Black rubber jacket	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	
181	Enameled wire	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	/	P
182	Black heat shrink tubing	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	
183	Black magnetosphere	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	/	P
184	Black rubber sheath	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	
185	White plastic cover1	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	
186	White plastic cover2	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	
187	Black sponge	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	
188	White plastic foundation	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	

No.	Test Sample	Screening Result						Verification Test Result												
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict	
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000 (d)	0.10 $\mu\text{g}/\text{cm}^2$ (e)	1000	1000	1000	1000	1000	1000	1000		
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50		
189	White fibre cloth	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
190	Green fibre cloth	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
191	White fixing glue	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
192	Black carbon filter screen	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
193	Transparent plastic filter screen	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
194	PCB base material	N.D.	N.D.	N.D.	N.D.	2.1 $\times 10^4$	V	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P
195	Silvery metal soldering tin	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
196	Chip resistance	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
197	Chip capacitance	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P

No.	Test Sample	Screening Result						Verification Test Result												
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict	
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000 (d)	0.10 $\mu\text{g}/\text{cm}^2$ (e)	1000	1000	1000	1000	1000	1000	1000		
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50		
198	Chip diode	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
199	Black chip	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
200	metal LED light	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
201	Black metal reel	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
202	Enameled wire	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
203	PCB base material	N.D.	N.D.	N.D.	N.D.	2.1 $\times 10^4$	V	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P
204	Silvery metal soldering tin	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
205	White plastic socket	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
206	Transparent closed switch	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P

No.	Test Sample	Screening Result						Verification Test Result													
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict		
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000 (d)	0.10 µg/cm <sup>2</sup> (e)	1000	1000	1000	1000	1000	1000	1000			
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50			
207	metal screwSilvery cladding material	N.D.	N.D.	N.D.	/	—	V	/	/	/	/	Negative	/	/	/	/	/	/	/	P	
208	metal screwSilvery base material	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	/	P
209	PCB base material	N.D.	N.D.	N.D.	N.D.	2.0 × 10 <sup>4</sup>	V	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P
210	Silvery metal soldering tin	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	/	P
211	Chip resistance	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P
212	Chip capacitance	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P
213	Chip diode	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P
214	Chip audion	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P
215	Black rectifier bridge	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P

No.	Test Sample	Screening Result						Verification Test Result													
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict		
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000 (d)	0.10 $\mu\text{g}/\text{cm}^2$ (e)	1000	1000	1000	1000	1000	1000	1000			
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50			
216	White nameplate	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P	
217	Silvery metal screening can	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	/	P
218	Gray rubber plug	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
219	White plastic bracket	N.D.	N.D.	N.D.	N.D.	2.0 $\times 10^4$	V	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P
220	Silvery metal illustration	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	/	P
221	Gray rubber sheath	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
222	Blue rubber jacket	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
223	Brown rubber jacket	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
224	Enameled wire	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	/	P

No.	Test Sample	Screening Result						Verification Test Result												
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict	
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000 (d)	0.10 µg/cm <sup>2</sup> (e)	1000	1000	1000	1000	1000	1000	1000		
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50		
225	Gray rubber shell	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
226	White plastic bracket	N.D.	N.D.	N.D.	N.D.	2.1 × 10 <sup>4</sup>	V	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P
227	Golden metal Pin	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
228	Blue plastic film	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
229	Silvery metal shell	N.D.	N.D.	N.D.	27265	—	V	/	/	/	N.D.	/	/	/	/	/	/	/	/	P
230	Black plastic shell	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
231	Black plastic bracket	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
232	PCB base material	N.D.	N.D.	N.D.	N.D.	2.4 × 10 <sup>4</sup>	V	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P
233	Silvery metal soldering tin	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P



No.	Test Sample	Screening Result						Verification Test Result												
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict	
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000 (d)	0.10 $\mu\text{g}/\text{cm}^2$ (e)	1000	1000	1000	1000	1000	1000	1000		
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50		
234	Chip resistance	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
235	Transparent glue	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
236	Black metal body (camera len)	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
237	Transparent glass camera len	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
238	Silvery metal spring	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
239	PCB base material	N.D.	N.D.	N.D.	N.D.	$2.5 \times 10^4$	V	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P
240	Silvery metal soldering tin	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
241	Chip resistance	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
242	Chip capacitance	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P

No.	Test Sample	Screening Result						Verification Test Result												
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict	
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000 (d)	0.10 µg/cm <sup>2</sup> (e)	1000	1000	1000	1000	1000	1000	1000		
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50		
243	Chip diode	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
244	Chip audion	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
245	Black optical pump	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
246	Black chip	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
247	Beige plastic connector	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
248	Black metal screw	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
249	Silvery trademark	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
250	Black plastic shell (impeller)	N.D.	N.D.	N.D.	N.D.	3.5 × 10 <sup>4</sup>	V	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P
251	PCB base material	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P

No.	Test Sample	Screening Result						Verification Test Result												
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict	
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000 (d)	0.10 µg/cm <sup>2</sup> (e)	1000	1000	1000	1000	1000	1000	1000		
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50		
252	Silvery metal soldering tin	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
253	Black plastic impeller	N.D.	N.D.	N.D.	N.D.	2.4 × 10 <sup>4</sup>	V	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P
254	Silvery metal axle	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
255	Silvery metal shell	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
256	Black magnet	/	/	/	/	—	V	N.D.	N.D.	N.D.	N.D.	/	/	/	/	/	/	/	/	P
257	Black cladding material (metal screw)	N.D.	N.D.	N.D.	/	—	V	/	/	/	/	Negative	/	/	/	/	/	/	/	P
258	Silvery base material (metal screw)	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
259	PCB base material	N.D.	N.D.	N.D.	N.D.	2.4 × 10 <sup>4</sup>	V	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P
260	Silvery metal soldering tin	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P

No.	Test Sample	Screening Result						Verification Test Result												
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict	
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000 (d)	0.10 $\mu\text{g}/\text{cm}^2$ (e)	1000	1000	1000	1000	1000	1000	1000		
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50		
261	Chip resistance	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
262	Black diode	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
263	Black audion	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
264	Black chip	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
265	Silvery metal chip	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
266	Yellow component	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
267	Gray rubber jacket	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
268	Red rubber jacket	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P
269	Black rubber jacket	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	P

No.	Test Sample	Screening Result						Verification Test Result												
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict	
Requirement(mg/kg)	b)	b)	b)	b)	b)	1000		100	1000	1000 (d)	0.10 $\mu\text{g}/\text{cm}^2$ (e)	1000	1000	1000	1000	1000	1000	1000		
MDL(mg/kg)	10	10	10	10	10	5		5	5	5	—	50	50	50	50	50	50	50		
270	Enameled wire	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
271	Beige plastic socket	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
272	White plastic buckle	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
273	Silvery metal battery	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
274	PCB base material	N.D.	N.D.	N.D.	N.D.	$2.1 \times 10^4$	V	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	P
275	Silvery metal soldering tin	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P
276	Chip resistance	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
277	Black chip	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P
278	Yellow plastic paper	N.D.	N.D.	N.D.	N.D.	N.D.	P	/	/	/	/	/	/	/	N.D.	N.D.	N.D.	N.D.	N.D.	P

No.	Test Sample	Screening Result						Verification Test Result												
		Pb	Cd	Hg	Cr	Br	Verdict	Pb	Cd	Hg	(Cr VI)		PBBs	PBDEs	DEHP	BBP	DBP	DIBP	Verdict	
Requirement(mg/kg)	b)	b)	b)	b)	b)	b)		1000	100	1000	1000 (d)	0.10 $\mu\text{g}/\text{cm}^2$ (e)	1000	1000	1000	1000	1000	1000		1000
MDL(mg/kg)	10	10	10	10	10	10		5	5	5	5	—	50	50	50	50	50	50		50
279	Copper metal terminal	N.D.	N.D.	N.D.	N.D.	—	P	/	/	/	/	/	/	/	/	/	/	/	/	P

Remarks: a) Screening results, "P" means "Pass", "F" means "Fail", "V" means "the need for chemical confirmation."

b) XRF Screening limits scope: Pb:  $P \leq 700 < V < 1300 \leq F$ ; Cd:  $P \leq 70 < V < 130 \leq F$ ; Hg:  $P \leq 700 < V < 1300 \leq F$ ;

Cr:  $P \leq 700 < V$ ; Br:  $P \leq 300 < V$ ; XRF does not apply to the direct determination of hexavalent chromium plating.

c) "N.D." means "Not Detected"; "/" means "untested"; "—" means "not applicable"

d) It is the hexavalent chromium limit of Metal substrates or non-metallic materials.

e) It is the hexavalent chromium limit of metal plating.

"Negative" means "the Cr(VI) concentration is less than  $0.10 \mu\text{g}/\text{cm}^2$ "; "Positive" means the Cr(VI) concentration detected in the boiling water extraction solution is equal to or greater than  $0.13 \mu\text{g}/\text{cm}^2$  with a sample surface area of  $50 \text{ cm}^2$  used.


f) "▲1" According to the declaration from client, Pb is exempted by EU RoHS Directive 2011/65/EU base on: Electrical and electronic components containing lead in a glass or ceramic other than dielectric ceramic in capacitors, e.g. piezoelectronic devices, or in a glass or ceramic matrix compound.

Sample Photos




Remark: /


# Sample split Photos




1




2




3




4~8



9




10~11



12



13~14



15~16



17~18




19



20~21



# Sample split Photos




22



23~27



28~40




41~65



66




67




68~123




124~125




126~159



160~176



177~184




185~193

### Sample split Photos



194~202




203~217



218~227



228~258



259~279

-----End of Report-----

# Important

1. The test report is invalid without the official stamp of CVC;
2. Any photocopies or part photocopies of the test report are forbidden without the written permission from CVC;
3. The test report is invalid without the signatures of Author and Reviewer;
4. The test report is invalid if altered;
5. Objections to the test report must be submitted to CVC within 15 days;
6. Generally, commission test is responsible for the tested samples only;
7. As for the test result, “N” or “—” means “not applicable” , “/ ” means “not testing” , “P” means “pass” , and “F” means “fail”.

Address: No.3,Tiantaiyi Road, Kaitai Avenue, Science City, Guangzhou, China

Tel: 020 32293888

Fax: 020 32293889

Post Code: 510663

E-mail: [office@cvc.org.cn](mailto:office@cvc.org.cn)

<http://www.cvc.org.cn>