



中国认可
国际互认
检测
TESTING
CNAS L0095

第 1 页共 21 页

No.: RZRS2021-0435

检测报告

产品名称: 720 冰箱除味器

委托单位: 柒贰零 (北京) 健康科技有限公司

检测类别: 委托检测

威凯检测技术有限公司

样品描述及说明

样品照片:



制 造 商: 柒贰零(北京)健康科技有限公司

制造商地址: 北京市海淀区黑泉路 8 号 1 幢 9 层 101-42、101-43 号(东升地区)

生 产 厂: 深圳市康弘环保技术有限公司

生产厂地址: 深圳市龙岗区园山街道横坪公路 89 号涌鑫工业厂区 1 号厂房

| 样品拆分清单 | | | | | |
|--------|-----------|-------|------|----------|----|
| 序号 | 组件/部件/元器件 | | 检测单元 | | 备注 |
| | 编号 | 名称 | 编号 | 名称 | |
| 1 | 1 | 外壳 | 1-1 | 绿色塑料外壳 | — |
| 2 | | | 1-2 | 灰色海绵垫 | — |
| 3 | | | 1-3 | 白色条形码纸 | — |
| 4 | | | 1-4 | 白色塑料盖 | — |
| 5 | | | 1-5 | 白色塑料按钮 | — |
| 6 | | | 1-6 | 淡灰色橡胶密封塞 | — |
| 7 | | | 1-7 | 白色塑料支架 | — |
| 8 | 2 | 风扇 | 2-1 | 黑色塑料固定架 | — |
| 9 | | | 2-2 | 黑色塑料风扇外壳 | — |
| 10 | | | 2-3 | 黑色塑料叶轮 | — |
| 11 | | | 2-4 | 银色金属轴 | — |
| 12 | | | 2-5 | 黑色磁铁 | — |
| 13 | | | 2-6 | 黑色塑料绕线架 | — |
| 14 | | | 2-7 | 银色金属硅钢片 | — |
| 15 | | | 2-8 | 铜色金属轴套 | — |
| 16 | | | 2-9 | 漆包线 | — |
| 17 | | | 2-10 | PCB 板基材 | — |
| 18 | | | 2-11 | 银色金属焊锡 | — |
| 19 | | | 2-12 | 贴片电阻 | — |
| 20 | | | 2-13 | 黑色芯片 | — |
| 21 | | | 2-14 | 黑色塑料粘纸 | — |
| 22 | | | 2-15 | 银色金属螺丝 | — |
| 23 | 3 | 臭氧发生器 | 3-1 | 黑色塑料外壳 | — |
| 24 | | | 3-2 | 黑色灌封胶 | — |
| 25 | | | 3-3 | 银色铭牌纸 | — |
| 26 | | | 3-4 | 黑色塑料支架 | — |
| 27 | | | 3-5 | 银色金属插片 | — |
| 28 | | | 3-6 | 银色金属盖 | — |
| 29 | 4 | 电池 | 4-1 | 银色电池外壳 | — |
| 30 | | | 4-2 | 黄色塑料膜 | — |
| 31 | | | 4-3 | PCB 板基材 | — |
| 32 | | | 4-4 | 银色金属焊锡 | — |
| 33 | | | 4-5 | 黑色芯片 | — |
| 34 | 5 | 主控板 | 5-1 | PCB 板基材 | — |
| 35 | | | 5-2 | 银色金属焊锡 | — |
| 36 | | | 5-3 | 贴片电容 | — |
| 37 | | | 5-4 | 贴片电阻 | — |
| 38 | | | 5-5 | 贴片二极管 | — |
| 39 | | | 5-6 | 贴片三极管 | — |
| 40 | | | 5-7 | 黑色芯片 | — |
| 41 | | | 5-8 | 米黄色塑料接插件 | — |
| 42 | | | 5-9 | 开关黑色塑料底壳 | — |

| 样品拆分清单 | | | | | |
|--------|-----------|------------|------|----------|-----|
| 序号 | 组件/部件/元器件 | | 检测单元 | | 备注 |
| | 编号 | 名称 | 编号 | 名称 | |
| 43 | 5 | 主控板 | 5-10 | 银色金属支架 | — |
| 44 | | | 5-11 | 米黄色塑料按钮 | — |
| 45 | | | 5-12 | 银色金属振片 | — |
| 46 | | | 5-13 | 银色金属插头 | — |
| 47 | | | 5-14 | 透明 LED 灯 | — |
| 48 | | | 5-15 | 电解电容银色铝壳 | — |
| 49 | | | 5-16 | 黄色电解纸 | — |
| 50 | | | 5-17 | 银色塑料膜 | — |
| 51 | | | 5-18 | 黑色橡胶塞 | — |
| 52 | | | 5-19 | 黑色塑料底座 | — |
| 53 | | | 5-20 | 开关黑色塑料底壳 | — |
| 54 | | | 5-21 | 黑色塑料支架 | — |
| 55 | | | 5-22 | 黑色塑料按钮 | — |
| 56 | | | 5-23 | 银色金属振片 | — |
| 57 | | | 5-24 | 银色金属螺丝 | — |
| 58 | | | 6 | 线束组件 | 6-1 |
| 59 | 6-2 | 红色橡胶外被 | | | — |
| 60 | 6-3 | 黑色橡胶外被 (粗) | | | — |
| 61 | 6-4 | 白色橡胶外被 | | | — |
| 62 | 6-5 | 银色金属丝 | | | — |
| 63 | 6-6 | 白色塑料接插件 | | | — |
| 64 | 7 | 配件 | 7-1 | 透明塑料卡扣 | — |

检测结果及判定

| 序号 | 检测单元名称 | 筛选检测结果(mg/kg) | | | | | | 确证检测结果(mg/kg) | | | | | | 判定 | |
|----|----------|---------------|-------|-------|-----------------------|--------|------|---------------|-------|-------|------------------------|------|------------|------|--------------|
| | | 铅(Pb) | 镉(Cd) | 汞(Hg) | 总铬(Cr) | 总溴(Br) | 筛选判定 | 铅(Pb) | 镉(Cd) | 汞(Hg) | 六价铬(Cr ⁶⁺) | | 多溴联苯(PBBs) | | 多溴二苯醚(PBDEs) |
| | | | | | | | | | | | 金属镀层 | 其他材料 | | | |
| 1 | 绿色塑料外壳 | N.D. | N.D. | N.D. | N.D. | N.D. | P | / | / | / | / | / | / | / | P |
| 2 | 灰色海绵垫 | N.D. | N.D. | N.D. | N.D. | N.D. | P | / | / | / | / | / | / | / | P |
| 3 | 白色条形码纸 | N.D. | N.D. | N.D. | N.D. | 340 | V | / | / | / | / | / | N.D. | N.D. | P |
| 4 | 白色塑料盖 | N.D. | N.D. | N.D. | N.D. | N.D. | P | / | / | / | / | / | / | / | P |
| 5 | 白色塑料按钮 | N.D. | N.D. | N.D. | N.D. | 687 | V | / | / | / | / | / | N.D. | N.D. | P |
| 6 | 淡灰色橡胶密封塞 | N.D. | N.D. | N.D. | N.D. | N.D. | P | / | / | / | / | / | / | / | P |
| 7 | 白色塑料支架 | N.D. | N.D. | N.D. | N.D. | 584 | V | / | / | / | / | / | N.D. | N.D. | P |
| 8 | 黑色塑料固定架 | N.D. | N.D. | N.D. | N.D. | N.D. | P | / | / | / | / | / | / | / | P |
| 9 | 黑色塑料风扇外壳 | N.D. | N.D. | N.D. | N.D. | 765 | V | / | / | / | / | / | N.D. | N.D. | P |
| 10 | 黑色塑料叶轮 | N.D. | N.D. | N.D. | N.D. | 305 | V | / | / | / | / | / | N.D. | N.D. | P |
| 11 | 银色金属轴 | N.D. | N.D. | N.D. | 9.0 × 10 ⁴ | — | V | / | / | / | 阴性 | / | / | / | P |
| 12 | 黑色磁铁 | / | / | / | / | — | V | N.D. | N.D. | N.D. | 阴性 | / | / | / | P |
| 13 | 黑色塑料绕线架 | N.D. | N.D. | N.D. | N.D. | N.D. | P | / | / | / | / | / | / | / | P |
| 14 | 银色金属硅钢片 | N.D. | N.D. | N.D. | 1656 | — | V | / | / | / | 阴性 | / | / | / | P |

检测结果及判定

| 序号 | 检测单元名称 | 筛选检测结果(mg/kg) | | | | | | 确证检测结果(mg/kg) | | | | | | 判定 | |
|----|---------|---------------|-------|-------|-----------------------|--------|------|---------------|-------|-------|------------------------|------|------------|------|--------------|
| | | 铅(Pb) | 镉(Cd) | 汞(Hg) | 总铬(Cr) | 总溴(Br) | 筛选判定 | 铅(Pb) | 镉(Cd) | 汞(Hg) | 六价铬(Cr ⁶⁺) | | 多溴联苯(PBBs) | | 多溴二苯醚(PBDEs) |
| | | | | | | | | | | | 金属镀层 | 其他材料 | | | |
| 15 | 铜色金属轴套 | N.D. | N.D. | N.D. | N.D. | — | P | / | / | / | / | / | / | / | P |
| 16 | 漆包线 | N.D. | N.D. | N.D. | N.D. | — | P | / | / | / | / | / | / | / | P |
| 17 | PCB 板基材 | N.D. | N.D. | N.D. | N.D. | 414 | V | / | / | / | / | / | N.D. | N.D. | P |
| 18 | 银色金属焊锡 | N.D. | N.D. | N.D. | N.D. | — | P | / | / | / | / | / | / | / | P |
| 19 | 贴片电阻 | 978 | N.D. | N.D. | N.D. | N.D. | V | 462 | / | / | / | / | / | / | P |
| 20 | 黑色芯片 | N.D. | N.D. | N.D. | N.D. | N.D. | P | / | / | / | / | / | / | / | P |
| 21 | 黑色塑料粘纸 | N.D. | N.D. | N.D. | N.D. | N.D. | P | / | / | / | / | / | / | / | P |
| 22 | 银色金属螺丝 | N.D. | N.D. | N.D. | 7875 | — | V | / | / | / | 阴性 | / | / | / | P |
| 23 | 黑色塑料外壳 | N.D. | N.D. | N.D. | N.D. | 414 | V | / | / | / | / | / | N.D. | N.D. | P |
| 24 | 黑色灌封胶 | N.D. | N.D. | N.D. | N.D. | N.D. | P | / | / | / | / | / | / | / | P |
| 25 | 银色铭牌纸 | N.D. | N.D. | N.D. | N.D. | N.D. | P | / | / | / | / | / | / | / | P |
| 26 | 黑色塑料支架 | N.D. | N.D. | N.D. | N.D. | 406 | V | / | / | / | / | / | N.D. | N.D. | P |
| 27 | 银色金属插片 | N.D. | N.D. | N.D. | 8.9 × 10 ⁴ | — | V | / | / | / | 阴性 | / | / | / | P |
| 28 | 银色金属盖 | N.D. | N.D. | N.D. | 1.6 × 10 ⁵ | — | V | / | / | / | 阴性 | / | / | / | P |

检测结果及判定

| 序号 | 检测单元名称 | 筛选检测结果(mg/kg) | | | | | | 确证检测结果(mg/kg) | | | | | | | 判定 |
|----|----------|---------------|-------|-------|--------|-----------------------|------|---------------|-------|-------|------------------------|------|------------|--------------|----|
| | | 铅(Pb) | 镉(Cd) | 汞(Hg) | 总铬(Cr) | 总溴(Br) | 筛选判定 | 铅(Pb) | 镉(Cd) | 汞(Hg) | 六价铬(Cr ⁶⁺) | | 多溴联苯(PBBs) | 多溴二苯醚(PBDEs) | |
| | | | | | | | | | | | 金属镀层 | 其他材料 | | | |
| 29 | 银色电池外壳 | N.D. | N.D. | N.D. | N.D. | — | P | / | / | / | / | / | / | / | P |
| 30 | 黄色塑料膜 | N.D. | N.D. | N.D. | N.D. | N.D. | P | / | / | / | / | / | / | / | P |
| 31 | PCB 板基材 | N.D. | N.D. | N.D. | N.D. | 4.8 × 10 ⁴ | V | / | / | / | / | / | N.D. | N.D. | P |
| 32 | 银色金属焊锡 | N.D. | N.D. | N.D. | N.D. | — | P | / | / | / | / | / | / | / | P |
| 33 | 黑色芯片 | N.D. | N.D. | N.D. | N.D. | N.D. | P | / | / | / | / | / | / | / | P |
| 34 | PCB 板基材 | N.D. | N.D. | N.D. | N.D. | 7872 | V | / | / | / | / | / | N.D. | N.D. | P |
| 35 | 银色金属焊锡 | N.D. | N.D. | N.D. | N.D. | — | P | / | / | / | / | / | / | / | P |
| 36 | 贴片电容 | N.D. | N.D. | N.D. | N.D. | N.D. | P | / | / | / | / | / | / | / | P |
| 37 | 贴片电阻 | N.D. | N.D. | N.D. | N.D. | N.D. | P | / | / | / | / | / | / | / | P |
| 38 | 贴片二极管 | N.D. | N.D. | N.D. | N.D. | N.D. | P | / | / | / | / | / | / | / | P |
| 39 | 贴片三极管 | N.D. | N.D. | N.D. | N.D. | N.D. | P | / | / | / | / | / | / | / | P |
| 40 | 黑色芯片 | N.D. | N.D. | N.D. | N.D. | N.D. | P | / | / | / | / | / | / | / | P |
| 41 | 米黄色塑料接插件 | N.D. | N.D. | N.D. | N.D. | 433 | V | / | / | / | / | / | N.D. | N.D. | P |
| 42 | 开关黑色塑料底壳 | N.D. | N.D. | N.D. | N.D. | 424 | V | / | / | / | / | / | N.D. | N.D. | P |

检测结果及判定

| 序号 | 检测单元名称 | 筛选检测结果(mg/kg) | | | | | | 确证检测结果(mg/kg) | | | | | | 判定 | |
|----|----------|---------------|-------|-------|-----------------------|--------|------|---------------|-------|-------|------------------------|------|------------|------|--------------|
| | | 铅(Pb) | 镉(Cd) | 汞(Hg) | 总铬(Cr) | 总溴(Br) | 筛选判定 | 铅(Pb) | 镉(Cd) | 汞(Hg) | 六价铬(Cr ⁶⁺) | | 多溴联苯(PBBs) | | 多溴二苯醚(PBDEs) |
| | | | | | | | | | | | 金属镀层 | 其他材料 | | | |
| 43 | 银色金属支架 | N.D. | N.D. | N.D. | N.D. | — | P | / | / | / | / | / | / | / | P |
| 44 | 米黄色塑料按钮 | N.D. | N.D. | N.D. | N.D. | N.D. | P | / | / | / | / | / | / | / | P |
| 45 | 银色金属振片 | N.D. | N.D. | N.D. | 9.0 × 10 ⁴ | — | V | / | / | / | 阴性 | / | / | / | P |
| 46 | 银色金属插头 | N.D. | N.D. | N.D. | 1.1 × 10 ⁵ | — | V | / | / | / | 阴性 | / | / | / | P |
| 47 | 透明 LED 灯 | N.D. | N.D. | N.D. | N.D. | N.D. | P | / | / | / | / | / | / | / | P |
| 48 | 电解电容银色铝壳 | N.D. | N.D. | N.D. | N.D. | — | P | / | / | / | / | / | / | / | P |
| 49 | 黄色电解纸 | N.D. | N.D. | N.D. | N.D. | N.D. | P | / | / | / | / | / | / | / | P |
| 50 | 银色塑料膜 | N.D. | N.D. | N.D. | N.D. | N.D. | P | / | / | / | / | / | / | / | P |
| 51 | 黑色橡胶塞 | N.D. | N.D. | N.D. | N.D. | N.D. | P | / | / | / | / | / | / | / | P |
| 52 | 黑色塑料底座 | N.D. | N.D. | N.D. | N.D. | 286 | V | / | / | / | / | / | N.D. | N.D. | P |
| 53 | 开关黑色塑料底壳 | N.D. | N.D. | N.D. | N.D. | 511 | V | / | / | / | / | / | N.D. | N.D. | P |
| 54 | 黑色塑料支架 | N.D. | N.D. | N.D. | N.D. | — | P | / | / | / | / | / | / | / | P |
| 55 | 黑色塑料按钮 | N.D. | N.D. | N.D. | N.D. | N.D. | P | / | / | / | / | / | / | / | P |
| 56 | 银色金属振片 | N.D. | N.D. | N.D. | 8.9 × 10 ⁴ | — | V | / | / | / | 阴性 | / | / | / | P |

检测结果及判定

| 序号 | 检测单元名称 | 筛选检测结果(mg/kg) | | | | | | 确证检测结果(mg/kg) | | | | | | 判定 | |
|----|-----------|---------------|-------|-------|--------|--------|------|---------------|-------|-------|------------------------|------|------------|------|--------------|
| | | 铅(Pb) | 镉(Cd) | 汞(Hg) | 总铬(Cr) | 总溴(Br) | 筛选判定 | 铅(Pb) | 镉(Cd) | 汞(Hg) | 六价铬(Cr ⁶⁺) | | 多溴联苯(PBBs) | | 多溴二苯醚(PBDEs) |
| | | | | | | | | | | | 金属镀层 | 其他材料 | | | |
| 57 | 银色金属螺丝 | N.D. | N.D. | N.D. | 1120 | — | V | / | / | / | 阴性 | / | / | / | P |
| 58 | 黑色橡胶外被(细) | N.D. | N.D. | N.D. | N.D. | 256 | V | / | / | / | / | / | N.D. | N.D. | P |
| 59 | 红色橡胶外被 | N.D. | N.D. | N.D. | N.D. | N.D. | P | / | / | / | / | / | / | / | P |
| 60 | 黑色橡胶外被(粗) | N.D. | N.D. | N.D. | N.D. | 275 | V | / | / | / | / | / | N.D. | N.D. | P |
| 61 | 白色橡胶外被 | N.D. | N.D. | N.D. | N.D. | 816 | V | / | / | / | / | / | N.D. | N.D. | P |
| 62 | 银色金属丝 | N.D. | N.D. | N.D. | N.D. | — | P | / | / | / | / | / | / | / | P |
| 63 | 白色塑料接插件 | N.D. | N.D. | N.D. | N.D. | N.D. | P | / | / | / | / | / | / | / | P |
| 64 | 透明塑料卡扣 | N.D. | N.D. | N.D. | N.D. | 642 | V | / | / | / | / | / | N.D. | N.D. | P |

备注:

- 1) 对于 PBBs 和 PBDEs, 其筛选检测结果显示的是总 Br 含量, 对于 Cr⁶⁺, 其筛选检测结果显示的是总 Cr 含量;
- 2) “P”表示“通过”, “F”表示“不通过”, “V”表示“需进行确证检测”;
- 3) 筛选检测的限值范围见下表:

单位: mg/kg

| 检测物质 | 聚合物 | 金属材料 | 复合材料 |
|------|----------------|----------------|----------------|
| Cd | P≤50<V<150≤F | P≤50<V<150≤F | P≤10<V<170≤F |
| Pb | P≤500<V<1500≤F | P≤500<V<1500≤F | P≤300<V<1700≤F |
| Hg | P≤500<V<1500≤F | P≤500<V<1500≤F | P≤300<V<1700≤F |
| Br | P≤200<V | — | P≤150<V |
| Cr | P≤500<V | P≤500<V | P≤300<V |

- 4) “N.D.”表示“未检出 (低于报告限)”, “/”表示“未检测”, “—”表示“不适用”;
- 5) 筛选检测各检测物质的报告限见下表:

单位: mg/kg

| 检测物质 | Cd | Pb | Hg | 总 Br | 总 Cr |
|------|----|----|----|------|------|
| 报告限 | 10 | 10 | 10 | 10 | 10 |

- 6) 确证检测的限值和报告限见下表:

单位: mg/kg

| 检测物质 | Cd | Pb | Hg | 其他材料中的 Cr ⁶⁺ | 金属镀层中的 Cr ⁶⁺ | PBBs | PBDEs |
|------|-----|------|------|-------------------------|-------------------------|------|-------|
| 限值 | 100 | 1000 | 1000 | 1000 | 见备注 7) | 1000 | 1000 |
| 报告限 | 5 | 5 | 5 | 5 | | 50 | 50 |

- 7) 金属防腐镀层 Cr⁶⁺检测结果的表述为: 由表面积为 50cm² 的样品所萃取出来的溶液中测得的六价铬的浓度, 阴性表示六价铬小于 0.10 μg/cm², 判定为: 阴性 (Negative), 样品合格; 阳性表示六价铬大于 0.13 μg/cm², 判定为: 阳性 (Positive), 样品不合格。

检测结果及判定

| 序号 | 检测单元名称 | 确证检测结果 | | | | 判定 |
|----|----------|-----------------------|----------------|---------------|-----------------|----|
| | | 邻苯二甲酸二(2-乙基己基酯)(DEHP) | 邻苯二甲酸二丁苄酯(BBP) | 邻苯二甲酸二丁酯(DBP) | 邻苯二甲酸二异丁酯(DIBP) | |
| 1 | 绿色塑料外壳 | N.D. | N.D. | N.D. | N.D. | P |
| 2 | 灰色海绵垫 | N.D. | N.D. | N.D. | N.D. | P |
| 3 | 白色条形码纸 | N.D. | N.D. | N.D. | N.D. | P |
| 4 | 白色塑料盖 | N.D. | N.D. | N.D. | N.D. | P |
| 5 | 白色塑料按钮 | N.D. | N.D. | N.D. | N.D. | P |
| 6 | 淡灰色橡胶密封塞 | N.D. | N.D. | N.D. | N.D. | P |
| 7 | 白色塑料支架 | N.D. | N.D. | N.D. | N.D. | P |
| 8 | 黑色塑料固定架 | N.D. | N.D. | N.D. | N.D. | P |
| 9 | 黑色塑料风扇外壳 | N.D. | N.D. | N.D. | N.D. | P |
| 10 | 黑色塑料叶轮 | N.D. | N.D. | N.D. | N.D. | P |
| 11 | 银色金属轴 | / | / | / | / | / |
| 12 | 黑色磁铁 | / | / | / | / | / |
| 13 | 黑色塑料绕线架 | N.D. | N.D. | N.D. | N.D. | P |
| 14 | 银色金属硅钢片 | / | / | / | / | / |
| 15 | 铜色金属轴套 | / | / | / | / | / |

检测结果及判定

| 序号 | 检测单元名称 | 确证检测结果 | | | | 判定 |
|----|---------|-----------------------|----------------|---------------|-----------------|----|
| | | 邻苯二甲酸二(2-乙基己基酯)(DEHP) | 邻苯二甲酸二丁苄酯(BBP) | 邻苯二甲酸二丁酯(DBP) | 邻苯二甲酸二异丁酯(DIBP) | |
| 16 | 漆包线 | / | / | / | / | / |
| 17 | PCB 板基材 | N.D. | N.D. | N.D. | N.D. | P |
| 18 | 银色金属焊锡 | / | / | / | / | / |
| 19 | 贴片电阻 | N.D. | N.D. | N.D. | N.D. | P |
| 20 | 黑色芯片 | N.D. | N.D. | N.D. | N.D. | P |
| 21 | 黑色塑料粘纸 | N.D. | N.D. | N.D. | N.D. | P |
| 22 | 银色金属螺丝 | / | / | / | / | / |
| 23 | 黑色塑料外壳 | N.D. | N.D. | N.D. | N.D. | P |
| 24 | 黑色灌封胶 | N.D. | N.D. | N.D. | N.D. | P |
| 25 | 银色铭牌纸 | N.D. | N.D. | N.D. | N.D. | P |
| 26 | 黑色塑料支架 | N.D. | N.D. | N.D. | N.D. | P |
| 27 | 银色金属插片 | / | / | / | / | / |
| 28 | 银色金属盖 | / | / | / | / | / |
| 29 | 银色电池外壳 | / | / | / | / | / |
| 30 | 黄色塑料膜 | N.D. | N.D. | N.D. | N.D. | P |

检测结果及判定

| 序号 | 检测单元名称 | 确证检测结果 | | | | 判定 |
|----|----------|-----------------------|----------------|---------------|-----------------|----|
| | | 邻苯二甲酸二(2-乙基己基酯)(DEHP) | 邻苯二甲酸二丁苄酯(BBP) | 邻苯二甲酸二丁酯(DBP) | 邻苯二甲酸二异丁酯(DIBP) | |
| 31 | PCB 板基材 | N.D. | N.D. | N.D. | N.D. | P |
| 32 | 银色金属焊锡 | / | / | / | / | / |
| 33 | 黑色芯片 | N.D. | N.D. | N.D. | N.D. | P |
| 34 | PCB 板基材 | N.D. | N.D. | N.D. | N.D. | P |
| 35 | 银色金属焊锡 | / | / | / | / | / |
| 36 | 贴片电容 | N.D. | N.D. | N.D. | N.D. | P |
| 37 | 贴片电阻 | N.D. | N.D. | N.D. | N.D. | P |
| 38 | 贴片二极管 | N.D. | N.D. | N.D. | N.D. | P |
| 39 | 贴片三极管 | N.D. | N.D. | N.D. | N.D. | P |
| 40 | 黑色芯片 | N.D. | N.D. | N.D. | N.D. | P |
| 41 | 米黄色塑料接插件 | N.D. | N.D. | N.D. | N.D. | P |
| 42 | 开关黑色塑料底壳 | N.D. | N.D. | N.D. | N.D. | P |
| 43 | 银色金属支架 | / | / | / | / | / |
| 44 | 米黄色塑料按钮 | N.D. | N.D. | N.D. | N.D. | P |
| 45 | 银色金属振片 | / | / | / | / | / |

检测结果及判定

| 序号 | 检测单元名称 | 确证检测结果 | | | | 判定 |
|----|-----------|-----------------------|----------------|---------------|-----------------|----|
| | | 邻苯二甲酸二(2-乙基己基酯)(DEHP) | 邻苯二甲酸二丁苄酯(BBP) | 邻苯二甲酸二丁酯(DBP) | 邻苯二甲酸二异丁酯(DIBP) | |
| 46 | 银色金属插头 | / | / | / | / | / |
| 47 | 透明 LED 灯 | N.D. | N.D. | N.D. | N.D. | P |
| 48 | 电解电容银色铝壳 | / | / | / | / | / |
| 49 | 黄色电解纸 | N.D. | N.D. | N.D. | N.D. | P |
| 50 | 银色塑料膜 | N.D. | N.D. | N.D. | N.D. | P |
| 51 | 黑色橡胶塞 | N.D. | N.D. | N.D. | N.D. | P |
| 52 | 黑色塑料底座 | N.D. | N.D. | N.D. | N.D. | P |
| 53 | 开关黑色塑料底壳 | N.D. | N.D. | N.D. | N.D. | P |
| 54 | 黑色塑料支架 | / | / | / | / | / |
| 55 | 黑色塑料按钮 | N.D. | N.D. | N.D. | N.D. | P |
| 56 | 银色金属振片 | / | / | / | / | / |
| 57 | 银色金属螺丝 | / | / | / | / | / |
| 58 | 黑色橡胶外被(细) | N.D. | N.D. | N.D. | N.D. | P |
| 59 | 红色橡胶外被 | N.D. | N.D. | N.D. | N.D. | P |
| 60 | 黑色橡胶外被(粗) | N.D. | N.D. | N.D. | N.D. | P |

检测结果及判定

| 序号 | 检测单元名称 | 确证检测结果 | | | | 判定 |
|----|---------|---------------------------|--------------------|-------------------|---------------------|----|
| | | 邻苯二甲酸二(2-乙基己基酯) (DEHP) | 邻苯二甲酸二丁苄酯 (BBP) | 邻苯二甲酸二丁酯 (DBP) | 邻苯二甲酸二异丁酯 (DIBP) | |
| 61 | 白色橡胶外被 | N.D. | N.D. | N.D. | N.D. | P |
| 62 | 银色金属丝 | / | / | / | / | / |
| 63 | 白色塑料接插件 | N.D. | N.D. | N.D. | N.D. | P |
| 64 | 透明塑料卡扣 | N.D. | N.D. | N.D. | N.D. | P |

备注:

- 1) “P”表示“通过”, “F”表示“不通过”;
- 2) “N.D.”表示“未检出 (低于报告限)”, “/”表示“未检测”, “—”表示“不适用”;
- 3) 确证检测的限值和报告限见下表:


单位: mg/kg

| 检测物质 | DEHP | BBP | DBP | DIBP |
|------|------|------|------|------|
| 限值 | 1000 | 1000 | 1000 | 1000 |
| 报告限 | 10 | 10 | 10 | 10 |


组件/部件/元器件照片




1~3




4




5



6




7



8


组件/部件/元器件照片




9~21




22




23~25



26~28




29~33




34~46


组件/部件/元器件照片




47~56



57



58~63



64

注意事项 Important

1. 报告无检测单位印章无效;

The test report is invalid without the official stamp of CVC;

2. 未经本试验室书面同意, 不得部分地复制本报告;

Any part photocopies of the test report are forbidden without the written permission from CVC;

3. 报告无主检、审核、批准人签名无效;

The test report is invalid without the signatures of Author and Reviewer;

4. 报告涂改无效;

The test report is invalid if altered;

5. 对检测报告若有异议, 请于收到报告之日起十五天内向检测单位提出;

Objections to the test report must be submitted to CVC within 15 days;

6. 一般情况, 委托检测结果仅对所检测样品有效;

Generally, commission test is responsible for the tested samples only;

7. 检测结果中“—”或“N”表示“不适用”, “/”表示“未检测”, “P”表示“通过”或“合格”, “F”表示“不通过”或“不合格”。

As for the test result, “—” or “N” means “not applicable”, “/” means “not testing”, “P” means “pass” and “F” means “fail”.

报告中未加 CMA 标志时, 检测数据和结果仅供科研、教学或内部质量控制之用。

The test data and test results given in this test report should only be used for purposes of scientific research, teaching and internal quality control when the CMA symbol is not presented.

地址: 中国广州市科学城开泰大道天泰一路 3 号

电话: 020 32293888

传真: 020 32293889

邮政编码: 510663

电子邮箱: office@cvc.org.cn

网址: <http://www.cvc.org.cn>